

TEST REPORT

Mechanical & Hardgoods Laboratory

Report No. : HL30277A/2016

Page : 1 of 2

Date : MAR. 18, 2016

JER-YEU INDUSTRIAL CO., LTD.

No.367, Sec.3, Zhongshan Rd., Tanzi Dist., Taichung City, 42749 Taiwan

The following merchandise was submitted and identified by the applicant as:

Product Description: PTFE AIR HOSE
Manufacturer/Vendor: JER-YEU INDUSTRIAL CO., LTD.
Country of Origin: Taiwan

We have tested the submitted sample(s) as requested and the following results were obtained:


Test Requested: High Temperature Test

Test Method & Result: ---See following sheet(s)---

Date of Receipt: Mar. 11, 2016

Testing Period: Mar. 11, 2016 ~ Mar. 18, 2016

Signed for and on behalf of
SGS Taiwan Ltd.



Brian Huang
Team Leader



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested

TEST REPORT

Mechanical & Hardgoods Laboratory

Report No. : HL30277A/2016

Page : 2 of 2

Test Method:

- (a) Set the oven at the designated temperature by the client until stabilization.
- (b) Place the sample into chamber for 2 hours.
- (c) Take out the sample and examine whether damage or not by visual check then record any findings.
- (d) Test Equipment: DENG YNG/DH 600

Test Result:

Sample	Temperature	Time	Result
PTFE AIR HOSE	250 °C	2 hours	No visual damage was found after testing.

– Picture(s) –



Photo A: Appearance of the sample

---End of Report---